Technical Data Sheet

SD KOREA
www.sd-korea.com

SUA-33LV

92, Muha-Ro, 110 Beon-Gil, Namyang-Eup,
Hwaseong-Si, Gyeonggi-Do, Korea
TEL : +82-31-356-2397 FAX : +82-31-356-2399

SUA-33LV is amine catalyst for adjusting foam reaction time - CT and RT

1. General Property

Appearance	Clear Liquid
Viscosity (25℃, cps)	200↓
Specific Gravity (25℃)	1.03 ± 0.02
Flash Point (℃)	110↑

2. Product Feature

- CT, cream time controller
- Amine shortage : slow CT/RT, less open-cell and air porosity
- Amine excess : quick CT/RT, more open-cell and foam split

3. Dosage

- 0.05 to 1.5 php

4. Quality Guarantee

- 1(one) year after shipping

5. Packing Unit

- 20kg in plastic bucket

6. Storage Condition

- Should be stored apart from water to prevent absorption
- Should be capped after using