Batch No: 202305
Grade : M-124C

specification	results	Standard Regulation
PH	5±1	ASTM D 1512
DBP Oil absorption	105 cm^3 /100gr	ASTM D 2414
Ash Content	0.02%	ASTM D 1506
BET Surface area	99 m^2 /g	BET
Average Original Partical Size(nm)	28±5	AFM / TEM
Relative tinting strength	114%	ASTM D 3265

packing : Bag of 10 kg on pallet (600)kg